



45GP004 HIGH DENSITY POLYETHYLENE FOR PIPE EXTRUSION

45GP004 is a natural coloured PE 80 (MRS 8 MPa*) material for pipe extrusion. It possesses bimodal molecular weight distribution, which improves processability.

This grade meets the MFI, Density & Hydrostatic strength requirements of material grade PE 80 as per IS: 4984:1995 on "High Density Polyethylene pipe for water supply-specification". The designation of the natural resin of 45GP004 is PE-ENA-C45-T006 as per IS: 7328-1992 and shall meet the same given in the amendment No. 2 of IS: 4984:1995. When incorporated with adequate quantity of carbon black as specified in clause 5.2.3 of IS: 4984:1995, will meet the requirements of the designation PE-EW-C45-T006 mentioned in the clause 5.2 of IS: 4984:1995.

The grade also conforms to ISO 4427 specifications as shown below: & has been certified for MRS > 8 MPa as per ISO 9080.

Property	Test Method	Unit	Remarks
Hydrostatic Pressure Test	ISO 1167	Hrs	
9 Mpa @20°C			> 100
4.6 Mpa@80°C			> 165
4.0 Mpa@80°C			> 1000
MRS	ISO TR9080	MPa	>8.0
SCG	ISO 13479	Hrs	> 165
RCP (S4)	ISO 13477	Bar	> 12

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C/5.0 Kg)	ASTM D1238	gm/10 min	0.45
Density (23°C)	ASTM D1505	gm/cm ³	0.945
Thermal Stability (O.I.T.) 200°C	ASTM D3895	Min	> 30
Tensile Strength at Yield	ASTM D638	MPa	27
Elongation at Break	ASTM D638	%	> 600
Flexural Modulus	ASTM D790	MPa	800
Notched Izod Impact Strength	ASTM D256	J/m	No Break
ESCR, F ₅₀	ASTM D1693	Hrs	> 1000

* Typical values not to be taken as specification

**Mechanical Properties are on Compression moulding



Applications

PE 80 pressure pipes

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product - Application & Technology Group, PRTC.

Swastik Mill Compound, V. N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

• The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of May, 2007