



LL20FA010

LINEAR LOW DENSITY POLYETHYLENE FOR FILM EXTRUSION GRADE

LL20FA010 is a Butene Comonomer based Linear Low Density Polyethylene (LLDPE) without antiblock & slip additive. The grade is designed for manufacturing lamination films.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C/2.16 kg)	ASTM D1238	gm/10 min	1.0
Density (23°C)	ASTM D1505	gm/cm ³	0.920
Tensile Strength at break (MD/TD)	ASTM D882	kg/cm ²	400/300
Elongation at break (MD/TD)	ASTM D882	%	700/800
Elmendorff Tear Strength (MD/TD)	ASTM D1922	gm/25 mic	225/500
Dart Drop Impact (F-50)	ASTM D1709/A	g/μm	3

* Typical values not to be taken as specification

** Typical values (Mechanical) with 40μ film made with 1.8mm die gap & 2.25 BUR

Applications

Lamination film.

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.